


TECHNICAL DATA SHEET



Straight corrugated sheet **RN657 – Sh 657 ELYX UV U Neutral** produced with polyester resin reinforced with fibreglass, in conformity to the following characteristics and technical norms:

<i>Reinforcement:</i>	Fibreglass												
<i>% fibreglass</i>	≥ 25% (internal method)												
<i>Weight :</i>	1,500 kg/m ² (tolerance ± 5%) (internal method)												
<i>Density:</i>	1,4 g/cm ³ (internal method)												
<i>Colour:</i>	Clear (other colors on request)												
<i>Superficial protection:</i>	Protection of the outer/inner surface , made with a transparent ANTI UV film in coextruded polyester bonded to the GRP surface during hot lamination, avoiding superficial abrasion/erosion.												
<i>Exercise temperature</i>	-40 °C ÷ +120 °C												
<i>Self-ignition temperature:</i>	ab. 400 °C												
<i>Reaction to fire:</i>	The standard GRP (Glassfibre Reinforced Polyester) laminates are not inflammable, but if exposed to a flame they burn, they do not drip. Euroclass: F												
<i>Thermal conductivity (λ):</i>	0,22 W/mK (internal method)												
<i>Heat transmission (U):</i>	220 W/m ² K (1 mm thickness)												
<i>Hardness Barcol:</i>	55 ÷ 60 (UNI EN 59)												
<i>Thermal linear expansion:</i>	3 x 10 ⁻⁵ °C ⁻¹ (UNI EN 1013)												
<i>Tensile modulus:</i>	5,5 ÷ 6,5 GPa (UNI EN ISO 527-4)												
<i>Overload evenly distributed:</i>	See loading chart												
<i>Water vapour permeability:</i>	1,5 x 10 ⁻⁵ mg (m h Pa) (UNI EN 1013)												
<i>Water absorption:</i>	<1%												
<i>Resistance to chemical agents:</i>	GRP laminates are not altered by the action of the following acids in the listed solutions depending on their concentration and on a testing temperature ranging from 30° to 50° C. <table style="width: 100%; border: none;"> <tr> <td>Acetic acid</td> <td style="text-align: center;">⇒ 5%</td> <td>Sulphuric acid</td> <td style="text-align: center;">⇒ 30%</td> </tr> <tr> <td>Chlorohydric acid</td> <td style="text-align: center;">⇒ 10%</td> <td>Ethyl alcohol</td> <td style="text-align: center;">⇒ 95%</td> </tr> <tr> <td>Nitric acid</td> <td style="text-align: center;">⇒ 10%</td> <td>Benzol</td> <td style="text-align: center;">⇒ 30%</td> </tr> </table>	Acetic acid	⇒ 5%	Sulphuric acid	⇒ 30%	Chlorohydric acid	⇒ 10%	Ethyl alcohol	⇒ 95%	Nitric acid	⇒ 10%	Benzol	⇒ 30%
Acetic acid	⇒ 5%	Sulphuric acid	⇒ 30%										
Chlorohydric acid	⇒ 10%	Ethyl alcohol	⇒ 95%										
Nitric acid	⇒ 10%	Benzol	⇒ 30%										

Product marked CE in accordance with EU regulation 305/2011, harmonized standard EN 1013 (valid for light transmitting sheet). System of assessment and verification of constancy of performance: 4.

*The choice of building material must fulfill the requirements of the laws in force. The GRP roofing laminates are **not walkable**. The installation and maintenance must be done respecting the safety rules.*

The information contained in this technical data sheet is based on present information and experiences and is correct and precise, as far as we know. The information has no meaning of quality guarantee as the employment conditions are not under our direct control.

Brianza Plastica S.p.A.

A Company with a Quality Management System UNI EN ISO 9001:2015 certified (certif. N° 106 SQP-IIP)